

## TITLE OF THE INVENTION

### Resist Composition and Patterning Process

5           This invention relates to a resist composition,  
typically chemically amplified positive resist composition  
suitable for the microfabrication of VLSI, comprising as the  
base resin a polymer containing an alkoxyalkyl (meth)acrylate  
having heat resistance as a reactive group which is  
10 decomposable under the action of an acid to increase  
solubility in alkali, the composition exhibiting shelf  
stability, a significantly high contrast of alkali  
dissolution rate before and after exposure, a high  
sensitivity, a high resolution and improved etch resistance.

15

## BACKGROUND OF THE INVENTION

While a number of recent efforts are being made to  
achieve a finer pattern rule in the drive for higher  
20 integration and operating speeds in LSI devices,  
deep-ultraviolet lithography is thought to hold particular  
promise as the next generation in microfabrication technology.  
Deep-UV lithography is capable of achieving a minimum feature  
size of 0.5  $\mu\text{m}$  or less and, when a resist having low light  
25 absorption is used, can form patterns with sidewalls that are  
nearly perpendicular to the substrate.

Recently developed acid-catalyzed chemical  
amplification positive resists, such as those described in  
JP-B 2-27660, JP-A 63-27829, USP 4,491,628 and USP 5,310,619,  
30 utilize a high-intensity KrF excimer laser as the deep-UV  
light source. These resists, with their excellent properties  
such as high sensitivity, high resolution, and good dry  
etching resistance, are especially promising for deep-UV  
lithography.

35           Such chemically amplified positive resists include  
two-component systems comprising a base resin and a photoacid  
generator, and three-component systems comprising a base

resin, a photoacid generator, and a dissolution inhibitor having acid labile groups.

For example, JP-A 62-115440 describes a resist material comprising poly-4-tert-butoxystyrene and a photoacid generator, and JP-A 3-223858 describes a similar  
5 two-component resist material comprising a resin bearing tert-butoxy groups within the molecule, in combination with a photoacid generator. JP-A 4-211258 describes a two-component resist material which is comprised of polyhydroxystyrene  
10 bearing methyl, isopropyl, tert-butyl, tetrahydropyranyl, and trimethylsilyl groups, together with a photoacid generator.

JP-A 6-100488 discloses a resist material comprised of a polydihydroxystyrene derivative, such as  
poly[3,4-bis(2-tetrahydropyranyloxy)styrene],  
15 poly[3,4-bis(tert-butoxycarbonyloxy)styrene] or poly[3,5-bis(2-tetrahydropyranyloxy)styrene], and a photoacid generator.


To provide higher transparency and firm adhesion to substrates and to improve footing on substrates and etching  
20 resistance, JP-A 3-275149 and JP-A 6-289608 propose resist materials using copolymers of hydroxystyrene with a tertiary ester of (meth)acrylic acid. The resist materials of this type were still unsatisfactory because of poor resolution and an indefinite pattern profile after exposure. A further  
25 approach is a resist composition comprising a copolymer of hydroxystyrene with ethoxyethyl (meth)acrylate, which exhibited high resolution, but remained impractical because of very low thermal stability.

### 30 SUMMARY OF THE INVENTION

An object of the invention is to provide a resist composition, especially chemically amplified positive resist composition, which is superior to prior art positive resist compositions in sensitivity, resolution, exposure latitude  
35 and process flexibility, and has a satisfactory pattern profile after exposure and thermal stability.




of the following general formula (2) and having a weight average molecular weight of 1,000 to 500,000.




Herein  $\text{R}^2$  is hydrogen, hydroxy, a straight or branched alkyl group, halogen atom or trifluoromethyl group.

In a further embodiment, the invention provides a resist composition comprising a polymer comprising recurring units of both the following general formulae (1) and (3) and having a weight average molecular weight of 1,000 to 500,000.




Herein  $\text{R}^1$ ,  $\text{R}^2$ ,  $\text{R}^3$ ,  $\text{R}^4$  and  $\text{R}^5$  are as defined above,  $t$  is a positive number.




Herein  $R^6$ ,  $R^7$ ,  $R^9$ ,  $R^{10}$  and  $R^{11}$  are each independently hydrogen, hydroxy, a straight or branched alkyl group, halogen atom or trifluoromethyl group,  $R^8$  is an alkyl group having 1 to 10 carbon atoms,  $R^{12}$  is an alkyl group having 4 to 30 carbon atoms or silicon-substituted alkyl group,  $q$ ,  $r$  and  $s$  are 0 or positive numbers, and  $p$  is a positive number.

In a still further embodiment, the invention provides a resist composition comprising a polymer comprising recurring units of both the following general formulae (2) and (3) and having a weight average molecular weight of 1,000 to 500,000.



Herein  $R^2$  and  $t$  are as defined above.



Herein  $R^6$ ,  $R^7$ ,  $R^8$ ,  $R^9$ ,  $R^{10}$ ,  $R^{11}$  and  $R^{12}$  and  $p$ ,  $q$ ,  $r$  and  $s$  are as defined above.

In another aspect, the invention provides a chemically amplified positive resist composition comprising (A) an organic solvent, (B) the polymer as a base resin, and (C) a photoacid generator, or a chemically amplified positive resist composition comprising (A) an organic solvent, (B) the polymer as a base resin, (C) a photoacid generator, and (D) a


dissolution inhibitor. The resist composition may further include (E) a basic compound.

In a further aspect, the invention provides a process for forming a resist pattern comprising the steps of applying the resist composition defined above onto a substrate to form a coating; heat treating the coating and then exposing it to high-energy radiation or electron beam through a photo mask; and optionally heat treating the exposed coating and developing it with a developer.


#### DESCRIPTION OF THE PREFERRED EMBODIMENT

##### Polymer


The resist compositions of the invention include polymers or high molecular weight compounds comprising recurring units of the following general formula (1) or (2), and optionally and additionally, recurring units of the following general formula (3), and having a weight average molecular weight of 1,000 to 500,000, as the base resin.



Herein  $\text{R}^1$  and  $\text{R}^2$  are each independently hydrogen, hydroxy, a straight or branched alkyl group, halogen atom or trifluoromethyl group.  $\text{R}^3$  is methyl or ethyl.  $\text{R}^4$  and  $\text{R}^5$  each are an alkyl group having 1 to 7 carbon atoms, or  $\text{R}^4$  and  $\text{R}^5$  may bond together to form a cyclic structure having 3 to 7 carbon atoms, especially 5 to 6 carbon atoms. The subscript  $t$  is a positive number.



Herein  $\text{R}^2$  is hydrogen, hydroxy, a straight or branched alkyl group, halogen atom or trifluoromethyl group, and  $t$  is a positive number.



Herein  $\text{R}^6$ ,  $\text{R}^7$ ,  $\text{R}^9$ ,  $\text{R}^{10}$  and  $\text{R}^{11}$  are each independently hydrogen, hydroxy, a straight or branched alkyl group, halogen atom or trifluoromethyl group,  $\text{R}^8$  is an alkyl group having 1 to 10 carbon atoms,  $\text{R}^{12}$  is an alkyl group having 4 to 30 carbon atoms or silicon-substituted alkyl group,  $q$ ,  $r$  and  $s$  are 0 or positive numbers, and  $p$  is a positive number.


The straight or branched alkyl groups are preferably those having 1 to 6 carbon atoms, especially 1 to 5 carbon atoms, for example, methyl, ethyl, propyl, isopropyl, n-butyl, iso-butyl and tert-butyl.

In formula (1),  $\text{R}^3$  is methyl or ethyl. When the thermal stability of the ester moiety is taken into account, methyl is most preferred and ethyl is next.

$\text{R}^4$  and  $\text{R}^5$  are each independently alkyl groups, of which methyl and ethyl are preferred. When  $\text{R}^4$  and  $\text{R}^5$ , taken together, form a cyclic structure, cyclohexyl and cyclopentyl groups are preferred. It is important for improving thermal

stability that R<sup>4</sup> and R<sup>5</sup> are alkyl groups rather than hydrogen atoms.

The units of formula (1) are exemplified below.



5 In formula (3), R<sup>8</sup> is an alkyl group, preferably methyl or ethyl. When R<sup>8</sup> serves as an acid labile group, tertiary alkyl groups having 4 to 10 carbon atoms such as t-butyl and t-amyl are preferred.

10 Of the halogen atoms represented by R<sup>1</sup>, R<sup>2</sup>, R<sup>6</sup>, R<sup>7</sup>, R<sup>9</sup>, R<sup>10</sup> and R<sup>11</sup>, fluorine, chlorine and bromine atoms are typical.

When the alkyl group represented by R<sup>12</sup> is a tertiary alkyl group, it is selected from a variety of such groups, preferably those groups of the general formulae (4) and (5) shown below.



15

Herein, R<sup>14</sup> is a methyl, ethyl, isopropyl, cyclohexyl, cyclopentyl, vinyl, acetyl, phenyl, benzyl or cyano group, and b is an integer of 0 to 3.

20 The cyclic alkyl groups of formula (4) are preferably 5-membered rings. Examples include 1-methylcyclopentyl, 1-ethylcyclopentyl, 1-isopropylcyclopentyl, 1-vinylcyclopentyl, 1-acetylcyclopentyl, 1-phenylcyclopentyl, 1-cyanocyclopentyl, 1-methylcyclohexyl, 1-ethylcyclohexyl, 1-isopropylcyclohexyl, 1-vinylcyclohexyl, 1-acetylcyclohexyl, 25 1-phenylcyclohexyl, and 1-cyanocyclohexyl.






Herein,  $\text{R}^{15}$  is a methyl, ethyl, isopropyl, cyclohexyl, cyclopentyl, vinyl, phenyl, benzyl or cyano group.

5 Illustrative examples of formula (5) include t-butyl, 1-vinyldimethyl, 1-benzoyldimethyl, 1-phenyldimethyl and 1-cyanodimethyl.

Those alkyl groups which form tertiary esters as illustrated below are also preferred as  $\text{R}^{12}$ .



10 (4)-1 (4)-2 (4)-3 (4)-4

Of the silicon-substituted alkyl groups represented by  $\text{R}^{12}$ , tris(trimethylsilyl)silylethyl, tris(trimethylsiloxy)silylethyl and trimethylsilylethyl groups are preferred.

In formulae (1), (2) and (3), t and p are positive  
 15 numbers, and q, r and s are 0 or positive numbers. In order for the resist composition to exhibit better properties, these subscripts should preferably satisfy the relationship:  
 $0 < t/(t+p+q+r+s) \leq 0.3$ , more preferably  $0.05 \leq t/(t+p+q+r+s) \leq 0.2$ ;  $0 < p/(t+p+q+r+s) \leq 0.8$ , more preferably  $0.5 \leq$   
 20  $p/(t+p+q+r+s) \leq 0.8$ ;  $0 \leq q/(t+p+q+r+s) \leq 0.25$ ;  $0 \leq r/(t+p+q+r+s) \leq 0.35$ ; and  $0 \leq s/(t+p+q+r+s) \leq 0.25$ .

If  $t=0$ , meaning that the polymer does not contain the corresponding units, the contrast of alkali dissolution rate before and after exposure is lost, detracting from  
 25 resolution. If the proportion of p is too high, the alkali dissolution rate in unexposed areas may become too high.

When q and s are positive numbers, lithographic characteristics can be adjusted as desired by utilizing the inclusion of acid labile groups of two or more species. By properly selecting the values of p, q, r and s within the  
5 above range, the size and configuration of a resist pattern can be controlled as desired.

The polymer of the invention should have a weight average molecular weight (Mw) of 1,000 to 500,000, preferably 2,000 to 30,000. With too low a Mw, resists may be less  
10 resistant to heat. With too high a Mw, alkali solubility lowers and a footing phenomenon often occurs after pattern formation.

It is recommended that the multi-component copolymer of the invention have a controlled molecular weight  
15 dispersity (Mw/Mn). If a copolymer has a wide dispersity, it contains more fractions of low molecular weight and high molecular weight polymers and thus forms a pattern after exposure with foreign matter left thereon or its shape disrupted. The influence of a molecular weight and its  
20 dispersity becomes greater as the pattern rule becomes finer. In order that a resist composition be advantageously used in patterning features to a finer size, the multi-component copolymer should preferably be a narrow disperse one having a molecular weight dispersity of 1.0 to 2.0, especially 1.0 to  
25 1.7.

In one typical embodiment, the polymer can be synthesized by dissolving an acetoxystyrene monomer, an alkoxyalkyl (meth)acrylate monomer and an additional monomer in an organic solvent, adding a radical initiator thereto,  
30 heat polymerizing the monomers, and subjecting the resulting polymer to alkaline hydrolysis in an organic solvent for deblocking the acetoxo group, thereby forming a multi-component copolymer of hydroxystyrene, alkoxyalkyl (meth)acrylate and additional component. Examples of the  
35 organic solvent used in polymerization include toluene, benzene, tetrahydrofuran, diethyl ether, and dioxane. Representative of the polymerization initiator are

2,2'-azobisisobutyronitrile,  
2,2'-azobis(2,4-dimethylvaleronitrile),  
dimethyl-2,2'-azobis(2-methylpropionate), benzoyl peroxide and  
lauroyl peroxide. Polymerization may be effected by heating  
5 at about 50 to 80°C. The reaction time is usually about 2 to  
100 hours, preferably about 5 to 20 hours. The base used in  
the alkaline hydrolysis is selected from aqueous ammonia and  
triethylamine, to name a few. The reaction temperature is  
about -20°C to 100°C, preferably about 0 to 60°C. The  
10 reaction time is usually about 0.2 to 100 hours, preferably  
about 0.5 to 20 hours. It is noted that the synthesis  
procedure is not limited to the aforementioned.

#### Resist composition

The resist compositions of the invention are typically  
15 of the positive working type, and especially of the  
chemically amplified positive working type. In particular,  
the chemically amplified positive resist composition is  
comprised of (A) an organic solvent, (B) the polymer defined  
above as a base resin, and (C) a photoacid generator.  
20 Optionally, the composition further includes (D) a  
dissolution inhibitor and preferably (E) a basic compound.

In the chemically amplified, positive working resist  
composition of the invention, component (A) is an organic  
solvent. Illustrative, non-limiting, examples include butyl  
25 acetate, amyl acetate, cyclohexyl acetate, 3-methoxybutyl  
acetate, methyl ethyl ketone, methyl amyl ketone,  
cyclohexanone, cyclopentanone, 3-ethoxyethyl propionate,  
3-ethoxymethyl propionate, 3-methoxymethyl propionate, methyl  
acetoacetate, ethyl acetoacetate, diacetone alcohol, methyl  
30 pyruvate, ethyl pyruvate, propylene glycol monomethyl ether,  
propylene glycol monoethyl ether, propylene glycol monomethyl  
ether propionate, propylene glycol monoethyl ether  
propionate, ethylene glycol monomethyl ether, ethylene glycol  
monoethyl ether, diethylene glycol monomethyl ether,  
35 diethylene glycol monoethyl ether, 3-methyl-3-methoxybutanol,  
N-methylpyrrolidone, dimethylsulfoxide,  $\gamma$ -butyrolactone,  
propylene glycol methyl ether acetate, propylene glycol ethyl

ether acetate, propylene glycol propyl ether acetate, methyl lactate, ethyl lactate, propyl lactate, and tetramethylene sulfone. Of these, the propylene glycol alkyl ether acetates and alkyl lactates are especially preferred. The solvents  
5 may be used alone or in admixture of two or more. An exemplary useful solvent mixture is a mixture of a propylene glycol alkyl ether acetate and an alkyl lactate.

It is noted that the alkyl groups of the propylene glycol alkyl ether acetates are preferably those of 1 to 4  
10 carbon atoms, for example, methyl, ethyl and propyl, with methyl and ethyl being especially preferred. Since the propylene glycol alkyl ether acetates include 1,2- and 1,3-substituted ones, each includes three isomers depending on the combination of substituted positions, which may be  
15 used alone or in admixture. It is also noted that the alkyl groups of the alkyl lactates are preferably those of 1 to 4 carbon atoms, for example, methyl, ethyl and propyl, with methyl and ethyl being especially preferred.

When the propylene glycol alkyl ether acetate is used  
20 as the solvent, it preferably accounts for at least 50% by weight of the entire solvent. Also when the alkyl lactate is used as the solvent, it preferably accounts for at least 50% by weight of the entire solvent. When a mixture of propylene glycol alkyl ether acetate and alkyl lactate is used as the  
25 solvent, that mixture preferably accounts for at least 50% by weight of the entire solvent. In this solvent mixture, it is further preferred that the propylene glycol alkyl ether acetate is 60 to 95% by weight and the alkyl lactate is 40 to 5% by weight. A lower proportion of the propylene glycol  
30 alkyl ether acetate would invite a problem of inefficient coating whereas a higher proportion thereof would provide insufficient dissolution and allow for particle and foreign matter formation. A lower proportion of the alkyl lactate would provide insufficient dissolution and cause the problem  
35 of many particles and foreign matter whereas a higher proportion thereof would lead to a composition which has a too high viscosity to apply and loses storage stability.

Usually the solvent is used in amounts of about 300 to 2,000 parts, preferably about 400 to 1,000 parts by weight per 100 parts by weight of the solids in the chemically amplified positive resist composition. The concentration is not limited to this range as long as film formation by existing methods is possible.

The photoacid generator (C) is a compound capable of generating an acid upon exposure to high energy radiation. Preferred photoacid generators are sulfonium salts, iodonium salts, sulfonyldiazomethanes, and N-sulfonyloxyimides. These photoacid generators are illustrated below while they may be used alone or in admixture of two or more.

Sulfonium salts are salts of sulfonium cations with sulfonates. Exemplary sulfonium cations include triphenylsulfonium, (4-tert-butoxyphenyl)diphenylsulfonium, bis(4-tert-butoxyphenyl)phenylsulfonium, tris(4-tert-butoxyphenyl)sulfonium, (3-tert-butoxyphenyl)diphenylsulfonium, bis(3-tert-butoxyphenyl)phenylsulfonium, tris(3-tert-butoxyphenyl)sulfonium, (3,4-di-tert-butoxyphenyl)diphenylsulfonium, bis(3,4-di-tert-butoxyphenyl)phenylsulfonium, tris(3,4-di-tert-butoxyphenyl)sulfonium, diphenyl(4-thiophenoxyphenyl)sulfonium, (4-tert-butoxycarbonylmethyloxyphenyl)diphenylsulfonium, tris(4-tert-butoxycarbonylmethyloxyphenyl)sulfonium, (4-tert-butoxyphenyl)bis(4-dimethylaminophenyl)sulfonium, tris(4-dimethylaminophenyl)sulfonium, 2-naphthyl diphenylsulfonium, dimethyl-2-naphthylsulfonium, 4-hydroxyphenyldimethylsulfonium, 4-methoxyphenyldimethylsulfonium, trimethylsulfonium, 2-oxocyclohexylcyclohexylmethylsulfonium, trinaphthylsulfonium, and tribenzylsulfonium. Exemplary sulfonates include trifluoromethanesulfonate, nonafluorobutanesulfonate, heptadecafluorooctanesulfonate, 2,2,2-trifluoroethanesulfonate, pentafluorobenzenesulfonate,

4-trifluoromethylbenzenesulfonate, 4-fluorobenzenesulfonate, toluenesulfonate, benzenesulfonate, 4,4-toluenesulfonyloxybenzenesulfonate, naphthalenesulfonate, camphorsulfonate, octanesulfonate, dodecylbenzenesulfonate, butanesulfonate, and methanesulfonate. Sulfonium salts based on combination of the foregoing examples are included.

Iodinium salts are salts of iodonium cations with sulfonates. Exemplary iodonium cations are aryliodonium cations including diphenyliodonium, bis(4-tert-butylphenyl)iodonium, 4-tert-butoxyphenylphenyliodonium, and 4-methoxyphenylphenyliodonium. Exemplary sulfonates include trifluoromethanesulfonate, nonafluorobutanesulfonate, heptadecafluorooctanesulfonate, 2,2,2-trifluoroethanesulfonate, pentafluorobenzenesulfonate, 4-trifluoromethylbenzenesulfonate, 4-fluorobenzenesulfonate, toluenesulfonate, benzenesulfonate, 4,4-toluenesulfonyloxybenzenesulfonate, naphthalenesulfonate, camphorsulfonate, octanesulfonate, dodecylbenzenesulfonate, butanesulfonate, and methanesulfonate. Iodonium salts based on combination of the foregoing examples are included.

Exemplary sulfonyldiazomethane compounds include bissulfonyldiazomethane compounds and sulfonyl-carbonyldiazomethane compounds such as bis(ethylsulfonyl)diazomethane, bis(1-methylpropylsulfonyl)diazomethane, bis(2-methylpropylsulfonyl)diazomethane, bis(1,1-dimethylethylsulfonyl)diazomethane, bis(cyclohexylsulfonyl)diazomethane, bis(perfluoroisopropylsulfonyl)diazomethane, bis(phenylsulfonyl)diazomethane, bis(4-methylphenylsulfonyl)diazomethane, bis(2,4-dimethylphenylsulfonyl)diazomethane, bis(2-naphthylsulfonyl)diazomethane, 4-methylphenylsulfonylbenzoyldiazomethane, tert-butylcarbonyl-4-methylphenylsulfonyldiazomethane, 2-naphthylsulfonylbenzoyldiazomethane,

4-methylphenylsulfonyl-2-naphthoyldiazomethane,  
methylsulfonylbenzoyldiazomethane, and  
tert-butoxycarbonyl-4-methylphenylsulfonyldiazomethane.

N-sulfonyloxyimide photoacid generators include  
5 combinations of imide skeletons with sulfonates. Exemplary  
imide skeletons are succinimide, naphthalene dicarboxylic  
acid imide, phthalimide, cyclohexyldicarboxylic acid imide,  
5-norbornene-2,3-dicarboxylic acid imide, and  
7-oxabicyclo[2.2.1]-5-heptene-2,3-dicarboxylic acid imide.  
10 Exemplary sulfonates include trifluoromethanesulfonate,  
nonafluorobutanesulfonate, heptafluorooctanesulfonate,  
2,2,2-trifluoroethanesulfonate, pentafluorobenzenesulfonate,  
4-trifluoromethylbenzenesulfonate, 4-fluorobenzenesulfonate,  
toluenesulfonate, benzenesulfonate, naphthalenesulfonate,  
15 camphorsulfonate, octanesulfonate, dodecylbenzenesulfonate,  
butanesulfonate, and methanesulfonate.

Benzoin sulfonate photoacid generators include benzoin  
tosylate, benzoin mesylate, and benzoin butanesulfonate.

Pyrogallol trisulfonate photoacid generators include  
20 pyrogallol, fluoroglycine, catechol, resorcinol, and  
hydroquinone, in which all the hydroxyl groups are replaced  
by trifluoromethanesulfonate, nonafluorobutanesulfonate,  
heptafluorooctanesulfonate,  
2,2,2-trifluoroethanesulfonate, pentafluorobenzenesulfonate,  
25 4-trifluoromethylbenzenesulfonate, 4-fluorobenzenesulfonate,  
toluenesulfonate, benzenesulfonate, naphthalenesulfonate,  
camphorsulfonate, octanesulfonate, dodecylbenzenesulfonate,  
butanesulfonate, and methanesulfonate.

Nitrobenzyl sulfonate photoacid generators include  
30 2,4-dinitrobenzyl sulfonate, 2-nitrobenzyl sulfonate, and  
2,6-dinitrobenzyl sulfonate, with exemplary sulfonates  
including trifluoromethanesulfonate,  
nonafluorobutanesulfonate, heptafluorooctanesulfonate,  
2,2,2-trifluoroethanesulfonate, pentafluorobenzenesulfonate,  
35 4-trifluoromethylbenzenesulfonate, 4-fluorobenzenesulfonate,  
toluenesulfonate, benzenesulfonate, naphthalenesulfonate,  
camphorsulfonate, octanesulfonate, dodecylbenzenesulfonate,

butanesulfonate, and methanesulfonate. Also useful are analogous nitrobenzyl sulfonate compounds in which the nitro group on the benzyl side is replaced by a trifluoromethyl group.

5           Sulfone photoacid generators include  
bis(phenylsulfonyl)methane,  
bis(4-methylphenylsulfonyl)methane,  
bis(2-naphthylsulfonyl)methane,  
2,2-bis(phenylsulfonyl)propane,  
10 2,2-bis(4-methylphenylsulfonyl)propane,  
2,2-bis(2-naphthylsulfonyl)propane,  
2-methyl-2-(p-toluenesulfonyl)propiophenone,  
2-cyclohexylcarbonyl-2-(p-toluenesulfonyl)propane, and  
2,4-dimethyl-2-(p-toluenesulfonyl)pentan-3-one.

15           Photoacid generators in the form of glyoxime derivatives include  
bis-O-(p-toluenesulfonyl)- $\alpha$ -dimethylglyoxime,  
bis-O-(p-toluenesulfonyl)- $\alpha$ -diphenylglyoxime,  
bis-O-(p-toluenesulfonyl)- $\alpha$ -dicyclohexylglyoxime,  
20 bis-O-(p-toluenesulfonyl)-2,3-pentanedione glyoxime,  
bis-O-(p-toluenesulfonyl)-2-methyl-3,4-pentanedione glyoxime,  
bis-O-(n-butanesulfonyl)- $\alpha$ -dimethylglyoxime,  
bis-O-(n-butanesulfonyl)- $\alpha$ -diphenylglyoxime,  
bis-O-(n-butanesulfonyl)- $\alpha$ -dicyclohexylglyoxime,  
25 bis-O-(n-butanesulfonyl)-2,3-pentanedione glyoxime,  
bis-O-(n-butanesulfonyl)-2-methyl-3,4-pentanedione glyoxime,  
bis-O-(methanesulfonyl)- $\alpha$ -dimethylglyoxime,  
bis-O-(trifluoromethanesulfonyl)- $\alpha$ -dimethylglyoxime,  
bis-O-(1,1,1-trifluoroethanesulfonyl)- $\alpha$ -dimethylglyoxime,  
30 bis-O-(tert-butanesulfonyl)- $\alpha$ -dimethylglyoxime,  
bis-O-(perfluorooctanesulfonyl)- $\alpha$ -dimethylglyoxime,  
bis-O-(cyclohexylsulfonyl)- $\alpha$ -dimethylglyoxime,  
bis-O-(benzenesulfonyl)- $\alpha$ -dimethylglyoxime,  
bis-O-(p-fluorobenzenesulfonyl)- $\alpha$ -dimethylglyoxime,



bis-O-(p-tert-butylbenzenesulfonyl)- $\alpha$ -dimethylglyoxime,  
bis-O-(xylenesulfonyl)- $\alpha$ -dimethylglyoxime, and  
bis-O-(camphorsulfonyl)- $\alpha$ -dimethylglyoxime.

Of these photoacid generators, the sulfonium salts,  
5 bissulfonyldiazomethane compounds, and N-sulfonyloxyimide  
compounds are preferred.

While the anion of the optimum acid to be generated  
differs depending on the ease of scission of acid labile  
groups introduced in the polymer, an anion which is  
10 non-volatile and not extremely diffusive is generally chosen.  
The preferred anions include benzenesulfonic acid anions,  
toluenesulfonic acid anions,  
4,4-toluenesulfonyloxybenzenesulfonic acid anions,  
pentafluorobenzenesulfonic acid anions,  
15 2,2,2-trifluoroethanesulfonic acid anions,  
nonafluorobutanesulfonic acid anions,  
heptadecafluorooctanesulfonic acid anions, and  
camphorsulfonic acid anions.

In the chemically amplified positive resist  
20 composition, an appropriate amount of the photoacid generator  
(C) is 0.1 to 20 parts, more preferably 1 to 10 parts by  
weight per 100 parts by weight of the base resin (B) in the  
composition. The photoacid generators may be used alone or  
in admixture of two or more. The transmittance of the resist  
25 film can be controlled by using a photoacid generator having  
a low transmittance at the exposure wavelength and adjusting  
the amount of the photoacid generator added.

The dissolution inhibitor (D) is a compound having on  
the molecule at least two phenolic hydroxyl groups, in which  
30 an average of from 10 to 100 mol% of all the hydrogen atoms  
on the phenolic hydroxyl groups are replaced with acid labile  
groups. The compound has a weight average molecular weight  
within the range of 100 to 1,000, and preferably 150 to 800.  
The dissolution inhibitor may be formulated in an amount of 0  
35 to 50 parts, preferably 5 to 50 parts, and more preferably 10  
to 30 parts by weight, per 100 parts by weight of the base

resin, and may be used singly or as a mixture of two or more thereof. Less amounts of the dissolution inhibitor may fail to yield an improved resolution, whereas too much amounts would lead to slimming of the patterned film, and thus a  
5 decline in resolution.

Illustrative, non-limiting, examples of the dissolution inhibitor (D) which are useful herein include  
bis(4-(2'-tetrahydropyranyloxy)phenyl)methane,  
bis(4-(2'-tetrahydrofuranyloxy)phenyl)methane,  
10 bis(4-tert-butoxyphenyl)methane,  
bis(4-tert-butoxycarbonyloxyphenyl)methane,  
bis(4-tert-butoxycarbonylmethyloxyphenyl)methane,  
bis(4-(1'-ethoxyethoxy)phenyl)methane,  
bis(4-(1'-ethoxypropyloxy)phenyl)methane,  
15 2,2-bis(4'-(2"-tetrahydropyranyloxy))propane,  
2,2-bis(4'-(2"-tetrahydrofuranyloxy)phenyl)propane,  
2,2-bis(4'-tert-butoxyphenyl)propane,  
2,2-bis(4'-tert-butoxycarbonyloxyphenyl)propane,  
2,2-bis(4-tert-butoxycarbonylmethyloxyphenyl)propane,  
20 2,2-bis(4'-(1"-ethoxyethoxy)phenyl)propane,  
2,2-bis(4'-(1"-ethoxypropyloxy)phenyl)propane,  
tert-butyl 4,4-bis(4'-(2"-tetrahydropyranyloxy)phenyl)-  
valerate,  
tert-butyl 4,4-bis(4'-(2"-tetrahydrofuranyloxy)phenyl)-  
25 valerate,  
tert-butyl 4,4-bis(4'-tert-butoxyphenyl)valerate,  
tert-butyl 4,4-bis(4-tert-butoxycarbonyloxyphenyl)valerate,  
tert-butyl 4,4-bis(4'-tert-butoxycarbonylmethyloxyphenyl)-  
valerate,  
30 tert-butyl 4,4-bis(4'-(1"-ethoxyethoxy)phenyl)valerate,  
tert-butyl 4,4-bis(4'-(1"-ethoxypropyloxy)phenyl)valerate,  
tris(4-(2'-tetrahydropyranyloxy)phenyl)methane,  
tris(4-(2'-tetrahydrofuranyloxy)phenyl)methane,  
tris(4-tert-butoxyphenyl)methane,  
35 tris(4-tert-butoxycarbonyloxyphenyl)methane,  
tris(4-tert-butoxycarbonyloxymethylphenyl)methane,  
tris(4-(1'-ethoxyethoxy)phenyl)methane,

tris(4-(1'-ethoxypropyloxy)phenyl)methane,  
1,1,2-tris(4'-(2"-tetrahydropyranyloxy)phenyl)ethane,  
1,1,2-tris(4'-(2"-tetrahydrofuranyloxy)phenyl)ethane,  
1,1,2-tris(4'-tert-butoxyphenyl)ethane,  
5 1,1,2-tris(4'-tert-butoxycarbonyloxyphenyl)ethane,  
1,1,2-tris(4'-tert-butoxycarbonylmethyloxyphenyl)ethane,  
1,1,2-tris(4'-(1'-ethoxyethoxy)phenyl)ethane, and  
1,1,2-tris(4'-(1'-ethoxypropyloxy)phenyl)ethane.

The basic compound (E) is preferably a compound  
10 capable of suppressing the rate of diffusion when the acid  
generated by the photoacid generator diffuses within the  
resist film. The inclusion of this type of basic compound  
holds down the rate of acid diffusion within the resist film,  
resulting in better resolution. In addition, it suppresses  
15 changes in sensitivity following exposure and reduces  
substrate and environment dependence, as well as improving  
the exposure latitude and the pattern profile.

Examples of basic compounds include primary, secondary,  
and tertiary aliphatic amines, mixed amines, aromatic amines,  
20 heterocyclic amines, carboxyl group-bearing nitrogenous  
compounds, sulfonyl group-bearing nitrogenous compounds,  
hydroxyl group-bearing nitrogenous compounds, hydroxyphenyl  
group-bearing nitrogenous compounds, alcoholic nitrogenous  
compounds, amide derivatives, and imide derivatives.

25 Examples of suitable primary aliphatic amines include  
ammonia, methylamine, ethylamine, n-propylamine,  
isopropylamine, n-butylamine, isobutylamine, sec-butylamine,  
tert-butylamine, pentylamine, tert-amylamine,  
cyclopentylamine, hexylamine, cyclohexylamine, heptylamine,  
30 octylamine, nonylamine, decylamine, dodecylamine, cetylamine,  
methylenediamine, ethylenediamine, and tetraethylenepentamine.  
Examples of suitable secondary aliphatic amines include  
dimethylamine, diethylamine, di-n-propylamine,  
diisopropylamine, di-n-butylamine, diisobutylamine,  
35 di-sec-butylamine, dipentylamine, dicyclopentylamine,  
dihexylamine, dicyclohexylamine, diheptylamine, dioctylamine,  
dinonylamine, didecylamine, didodecylamine, dicetylamine,

N,N-dimethylmethylenediamine, N,N-dimethylethylenediamine, and N,N-dimethyltetraethylenepentamine. Examples of suitable tertiary aliphatic amines include trimethylamine, triethylamine, tri-n-propylamine, triisopropylamine, 5 tri-n-butylamine, triisobutylamine, tri-sec-butylamine, tripentylamine, tricyclopentylamine, trihexylamine, tricyclohexylamine, triheptylamine, trioctylamine, trinonylamine, tridecylamine, tridodecylamine, tricetylamine, N,N,N',N'-tetramethylmethylenediamine, 10 N,N,N',N'-tetramethylethylenediamine, and N,N,N',N'-tetramethyltetraethylenepentamine.

Examples of suitable mixed amines include dimethylethylamine, methylethylpropylamine, benzylamine, phenethylamine, and benzyldimethylamine. Examples of 15 suitable aromatic and heterocyclic amines include aniline derivatives (e.g., aniline, N-methylaniline, N-ethylaniline, N-propylaniline, N,N-dimethylaniline, 2-methylaniline, 3-methylaniline, 4-methylaniline, ethylaniline, propylaniline, trimethylaniline, 2-nitroaniline, 3-nitroaniline, 20 4-nitroaniline, 2,4-dinitroaniline, 2,6-dinitroaniline, 3,5-dinitroaniline, and N,N-dimethyltoluidine), diphenyl(p-tolyl)amine, methyldiphenylamine, triphenylamine, phenylenediamine, naphthylamine, diaminonaphthalene, pyrrole derivatives (e.g., pyrrole, 2H-pyrrole, 1-methylpyrrole, 25 2,4-dimethylpyrrole, 2,5-dimethylpyrrole, and N-methylpyrrole), oxazole derivatives (e.g., oxazole and isooxazole), thiazole derivatives (e.g., thiazole and isothiazole), imidazole derivatives (e.g., imidazole, 4-methylimidazole, and 4-methyl-2-phenylimidazole), pyrazole 30 derivatives, furazan derivatives, pyrroline derivatives (e.g., pyrroline and 2-methyl-1-pyrroline), pyrrolidine derivatives (e.g., pyrrolidine, N-methylpyrrolidine, pyrrolidinone, and N-methylpyrrolidone), imidazoline derivatives, imidazolidine derivatives, pyridine derivatives (e.g., pyridine, 35 methylpyridine, ethylpyridine, propylpyridine, butylpyridine, 4-(1-butylpentyl)pyridine, dimethylpyridine, trimethylpyridine, triethylpyridine, phenylpyridine,

3-methyl-2-phenylpyridine, 4-tert-butylpyridine, diphenylpyridine, benzylpyridine, methoxypyridine, butoxypyridine, dimethoxypyridine, 1-methyl-2-pyridine, 4-pyrrolidinopyridine, 1-methyl-4-phenylpyridine, 5 2-(1-ethylpropyl)pyridine, aminopyridine, and dimethylaminopyridine), pyridazine derivatives, pyrimidine derivatives, pyrazine derivatives, pyrazoline derivatives, pyrazolidine derivatives, piperidine derivatives, piperazine derivatives, morpholine derivatives, indole derivatives, 10 isoindole derivatives, 1H-indazole derivatives, indoline derivatives, quinoline derivatives (e.g., quinoline and 3-quinolinecarbonitrile), isoquinoline derivatives, cinnoline derivatives, quinazoline derivatives, quinoxaline derivatives, phthalazine derivatives, purine derivatives, pteridine 15 derivatives, carbazole derivatives, phenanthridine derivatives, acridine derivatives, phenazine derivatives, 1,10-phenanthroline derivatives, adenine derivatives, adenosine derivatives, guanine derivatives, guanosine derivatives, uracil derivatives, and uridine derivatives.

20       Examples of suitable carboxyl group-bearing nitrogenous compounds include aminobenzoic acid, indolecarboxylic acid, and amino acid derivatives (e.g. nicotinic acid, alanine, arginine, aspartic acid, glutamic acid, glycine, histidine, isoleucine, glycyllleucine, leucine, 25 methionine, phenylalanine, threonine, lysine, 3-aminopyrazine-2-carboxylic acid, and methoxyalanine).


Examples of suitable sulfonyl group-bearing nitrogenous compounds include 3-pyridinesulfonic acid and pyridinium p-toluenesulfonate. Examples of suitable hydroxyl 30 group-bearing nitrogenous compounds, hydroxyphenyl group-bearing nitrogenous compounds, and alcoholic nitrogenous compounds include 2-hydroxypyridine, aminocresol, 2,4-quinolinediol, 3-indolemethanol hydrate, monoethanolamine, diethanolamine, triethanolamine, N-ethyldiethanolamine, 35 N,N-diethylethanolamine, triisopropanolamine, 2,2'-iminodiethanol, 2-aminoethanol, 3-amino-1-propanol, 4-amino-1-butanol, 4-(2-hydroxyethyl)morpholine,

2-(2-hydroxyethyl)pyridine, 1-(2-hydroxyethyl)piperazine,  
 1-[2-(2-hydroxyethoxy)ethyl]piperazine, piperidine ethanol,  
 1-(2-hydroxyethyl)pyrrolidine,  
 1-(2-hydroxyethyl)-2-pyrrolidinone,  
 5 3-piperidino-1,2-propanediol, 3-pyrrolidino-1,2-propanediol,  
 8-hydroxyjulolidine, 3-quinuclidinol, 3-tropanol,  
 1-methyl-2-pyrrolidine ethanol, 1-aziridine ethanol,  
 N-(2-hydroxyethyl)phthalimide, and  
 N-(2-hydroxyethyl)isonicotinamide. Examples of suitable  
 10 amide derivatives include formamide, N-methylformamide,  
 N,N-dimethylformamide, acetamide, N-methylacetamide,  
 N,N-dimethylacetamide, propionamide, and benzamide. Suitable  
 imide derivatives include phthalimide, succinimide, and  
 maleimide.

15 In addition, basic compounds of the following general  
 formula (B)-1 may also be included alone or in admixture.



20 In the formula, n is equal to 1, 2 or 3; side chain X,  
 which may be the same or different, is independently selected  
 from groups of the following general formulas (X)-1 to (X)-3,  
 and two or three X's may bond together to form a ring; and  
 side chain Y, which may be the same or different, is  
 25 independently hydrogen or a straight, branched or cyclic  
 alkyl group of 1 to 20 carbon atoms which may contain a  
 hydroxyl group or ether.



In the formulas,  $\text{R}^{300}$ ,  $\text{R}^{302}$  and  $\text{R}^{305}$  are independently  
 30 straight or branched alkylene groups of 1 to 4 carbon atoms;

R<sup>301</sup> and R<sup>304</sup> are independently hydrogen or straight, branched or cyclic alkyl groups of 1 to 20 carbon atoms, which may contain one or more hydroxyl, ether, ester groups or lactone rings; R<sup>303</sup> is a single bond or a straight or branched  
5 alkylene group of 1 to 4 carbon atoms; and R<sup>306</sup> is a straight, branched or cyclic alkyl group of 1 to 20 carbon atoms which may contain one or more hydroxyl, ether, ester groups or lactone rings.

Illustrative examples of the compounds of formula  
10 (B)-1 include tris(2-methoxymethoxyethyl)amine,  
tris{2-(2-methoxyethoxy)ethyl}amine,  
tris{2-(2-methoxyethoxymethoxy)ethyl}amine,  
tris{2-(1-methoxyethoxy)ethyl}amine,  
tris{2-(1-ethoxyethoxy)ethyl}amine,  
15 tris{2-(1-ethoxypropoxy)ethyl}amine,  
tris[2-{2-(2-hydroxyethoxy)ethoxy}ethyl]amine,  
4,7,13,16,21,24-hexaoxa-1,10-diazabicyclo[8.8.8]hexacosane,  
4,7,13,18-tetraoxa-1,10-diazabicyclo[8.5.5]eicosane,  
1,4,10,13-tetraoxa-7,16-diazabicyclooctadecane,  
20 1-aza-12-crown-4, 1-aza-15-crown-5, 1-aza-18-crown-6,  
tris(2-formyloxyethyl)amine, tris(2-acetoxyethyl)amine,  
tris(2-propionyloxyethyl)amine, tris(2-butyryloxyethyl)amine,  
tris(2-isobutyryloxyethyl)amine, tris(2-valeryloxyethyl)amine,  
tris(2-pivaloyloxyethyl)amine,  
25 N,N-bis(2-acetoxyethyl)-2-(acetoxycetoxy)ethylamine,  
tris(2-methoxycarbonyloxyethyl)amine,  
tris(2-tert-butoxycarbonyloxyethyl)amine,  
tris[2-(2-oxopropoxy)ethyl]amine,  
tris[2-(methoxycarbonylmethyl)oxyethyl]amine,  
30 tris[2-(tert-butoxycarbonylmethyloxy)ethyl]amine,  
tris[2-(cyclohexyloxy carbonylmethyloxy)ethyl]amine,  
tris(2-methoxycarbonylethyl)amine,  
tris(2-ethoxycarbonylethyl)amine,  
N,N-bis(2-hydroxyethyl)-2-(methoxycarbonyl)ethylamine,  
35 N,N-bis(2-acetoxyethyl)-2-(methoxycarbonyl)ethylamine,  
N,N-bis(2-hydroxyethyl)-2-(ethoxycarbonyl)ethylamine,  
N,N-bis(2-acetoxyethyl)-2-(ethoxycarbonyl)ethylamine,

N,N-bis(2-hydroxyethyl)-2-(2-methoxyethoxycarbonyl)ethylamine,  
 N,N-bis(2-acetoxyethyl)-2-(2-methoxyethoxycarbonyl)ethylamine,  
 N,N-bis(2-hydroxyethyl)-2-(2-hydroxyethoxycarbonyl)ethylamine,  
 N,N-bis(2-acetoxyethyl)-2-(2-acetoxyethoxycarbonyl)ethylamine,  
 5 N,N-bis(2-hydroxyethyl)-2-[(methoxycarbonyl)methoxycarbonyl]-  
 ethylamine,  
 N,N-bis(2-acetoxyethyl)-2-[(methoxycarbonyl)methoxycarbonyl]-  
 ethylamine,  
 N,N-bis(2-hydroxyethyl)-2-(2-oxopropoxycarbonyl)ethylamine,  
 10 N,N-bis(2-acetoxyethyl)-2-(2-oxopropoxycarbonyl)ethylamine,  
 N,N-bis(2-hydroxyethyl)-2-(tetrahydrofurfuryloxycarbonyl)-  
 ethylamine,  
 N,N-bis(2-acetoxyethyl)-2-(tetrahydrofurfuryloxycarbonyl)-  
 ethylamine,  
 15 N,N-bis(2-hydroxyethyl)-2-[(2-oxotetrahydrofuran-3-yl)oxy-  
 carbonyl]ethylamine,  
 N,N-bis(2-acetoxyethyl)-2-[(2-oxotetrahydrofuran-3-yl)oxy-  
 carbonyl]ethylamine,  
 N,N-bis(2-hydroxyethyl)-2-(4-hydroxybutoxycarbonyl)ethylamine,  
 20 N,N-bis(2-formyloxyethyl)-2-(4-formyloxybutoxycarbonyl)-  
 ethylamine,  
 N,N-bis(2-formyloxyethyl)-2-(2-formyloxyethoxycarbonyl)-  
 ethylamine,  
 N,N-bis(2-methoxyethyl)-2-(methoxycarbonyl)ethylamine,  
 25 N-(2-hydroxyethyl)-bis[2-(methoxycarbonyl)ethyl]amine,  
 N-(2-acetoxyethyl)-bis[2-(methoxycarbonyl)ethyl]amine,  
 N-(2-hydroxyethyl)-bis[2-(ethoxycarbonyl)ethyl]amine,  
 N-(2-acetoxyethyl)-bis[2-(ethoxycarbonyl)ethyl]amine,  
 N-(3-hydroxy-1-propyl)-bis[2-(methoxycarbonyl)ethyl]amine,  
 30 N-(3-acetoxy-1-propyl)-bis[2-(methoxycarbonyl)ethyl]amine,  
 N-(2-methoxyethyl)-bis[2-(methoxycarbonyl)ethyl]amine,  
 N-butyl-bis[2-(methoxycarbonyl)ethyl]amine,  
 N-butyl-bis[2-(2-methoxyethoxycarbonyl)ethyl]amine,  
 N-methyl-bis(2-acetoxyethyl)amine,  
 35 N-ethyl-bis(2-acetoxyethyl)amine,  
 N-methyl-bis(2-pivaloyloxyethyl)amine,  
 N-ethyl-bis[2-(methoxycarbonyloxy)ethyl]amine,



N-ethyl-bis[2-(tert-butoxycarbonyloxy)ethyl]amine,  
tris(methoxycarbonylmethyl)amine,  
tris(ethoxycarbonylmethyl)amine,  
N-butyl-bis(methoxycarbonylmethyl)amine,  
5 N-hexyl-bis(methoxycarbonylmethyl)amine, and  
 $\beta$ -(diethylamino)- $\delta$ -valerolactone.

The basic compounds may be used alone or in admixture of two or more. The basic compound is preferably formulated in an amount of 0 to 2 parts, and especially 0.01 to 1 part  
10 by weight, per 100 parts by weight of the base resin in the resist composition. The use of more than 2 parts of the basis compound would result in too low a sensitivity.

In the resist composition, a surfactant may be added for improving coating characteristics. Illustrative,  
15 non-limiting, examples of the surfactant include nonionic surfactants, for example, polyoxyethylene alkyl ethers such as polyoxyethylene lauryl ether, polyoxyethylene stearyl ether, polyoxyethylene cetyl ether, and polyoxyethylene oleyl ether, polyoxyethylene alkylaryl ethers such as  
20 polyoxyethylene octylphenol ether and polyoxyethylene nonylphenol ether, polyoxyethylene polyoxypropylene block copolymers, sorbitan fatty acid esters such as sorbitan monolaurate, sorbitan monopalmitate, and sorbitan monostearate, and polyoxyethylene sorbitan fatty acid esters  
25 such as polyoxyethylene sorbitan monolaurate, polyoxyethylene sorbitan monopalmitate, polyoxyethylene sorbitan monostearate, polyoxyethylene sorbitan trioleate, and polyoxyethylene sorbitan tristearate; fluorochemical surfactants such as EFTOP EF301, EF303 and EF352 (Tohkem Products Co., Ltd.),  
30 Megaface F171, F172 and F173 (Dainippon Ink & Chemicals, Inc.), Florade FC430 and FC431 (Sumitomo 3M Co., Ltd.), Asahiguard AG710, Surflon S-381, S-382, SC101, SC102, SC103, SC104, SC105, SC106, Surfynol E1004, KH-10, KH-20, KH-30 and KH-40 (Asahi Glass Co., Ltd.); organosiloxane polymers KP341,  
35 X-70-092 and X-70-093 (Shin-Etsu Chemical Co., Ltd.), acrylic acid or methacrylic acid Polyflow No. 75 and No. 95 (Kyo-eisha Ushi Kagaku Kogyo Co., Ltd.). Inter alia, FC430, Surflon

S-381, Surfynol E1004, KH-20 and KH-30 are preferred. These surfactants may be used alone or in admixture.

In the resist composition, the surfactant is preferably formulated in an amount of up to 2 parts, and especially up to 1 part by weight, per 100 parts by weight of the base resin in the resist composition.

For the microfabrication of integrated circuits, any well-known lithography may be used to form a resist pattern from the resist composition of the invention.

The composition is applied onto a substrate (e.g., Si, SiO<sub>2</sub>, SiN, SiON, TiN, WSi, BPSG, SOG, organic anti-reflecting film, etc.) by a suitable coating technique such as spin coating, roll coating, flow coating, dip coating, spray coating or doctor coating. The coating is prebaked on a hot plate at a temperature of 60 to 150°C for about 1 to 10 minutes, preferably 80 to 120°C for 1 to 5 minutes. The resulting resist film is generally 0.1 to 2.0 μm thick. With a mask having a desired pattern placed above the resist film, the resist film is then exposed to actinic radiation, preferably having an exposure wavelength of up to 300 nm, such as UV, deep-UV, electron beams, x-rays, excimer laser light, γ-rays and synchrotron radiation in an exposure dose of about 1 to 200 mJ/cm<sup>2</sup>, preferably about 10 to 100 mJ/cm<sup>2</sup>. The film is further baked on a hot plate at 60 to 150°C for 1 to 5 minutes, preferably 80 to 120°C for 1 to 3 minutes (post-exposure baking = PEB).

Thereafter the resist film is developed with a developer in the form of an aqueous base solution, for example, 0.1 to 5%, preferably 2 to 3% aqueous solution of tetramethylammonium hydroxide (TMAH) for 0.1 to 3 minutes, preferably 0.5 to 2 minutes by conventional techniques such as dipping, puddling or spraying. In this way, a desired resist pattern is formed on the substrate. It is appreciated that the resist composition of the invention is best suited for micro-patterning using such actinic radiation as deep UV with a wavelength of 254 to 193 nm, vacuum UV with a wavelength of 157 nm, electron beams, soft x-rays, x-rays,

excimer laser light,  $\gamma$ -rays and synchrotron radiation. With any of the above-described parameters outside the above-described range, the process may sometimes fail to produce the desired pattern.

5

#### EXAMPLE

Examples of the invention are given below by way of illustration and not by way of limitation. The abbreviation AIBN is azobisisobutyronitrile, Mw is a weight average  
10 molecular weight, Mn is a number average molecular weight, Mw/Mn is a molecular weight dispersity, NMR is nuclear magnetic resonance, and GPC is gel permeation chromatography.

#### Synthesis Example 1

15 In a 2-liter flask were admitted 126.3 g of p-acetoxystyrene, 28.5 g of styrene, 10.6 g of methoxyisobutyl methacrylate and 400 g of toluene as a solvent. The reactor was cooled to -70°C in a nitrogen atmosphere, whereupon vacuum deaeration and nitrogen flow  
20 were repeated three times. The reactor was warmed up to room temperature, 7.9 g of AIBN was added as a polymerization initiator, and the reactor was further heated to 60°C, at which reaction was effected for 20 hours. The reaction solution was concentrated to a 1/2 volume and poured into a  
25 mixture of 4.5 liters methanol and 0.2 liter water for precipitation. The resulting white solids were filtered and vacuum dried at 40°C, obtaining 182 g of a white polymer. The polymer was dissolved in a mixture of 0.3 liter methanol and 0.35 liter tetrahydrofuran again, to which 200 g of  
30 triethylamine and 40 g of water were added to effect deblocking reaction. The reaction solution was neutralized with acetic acid, concentrated, and dissolved in 0.5 liter of acetone. Following precipitation, filtration and drying in the same way as above, 127 g of a white polymer was obtained.  
35 The polymer was analyzed by  $^{13}\text{C}$ -NMR,  $^1\text{H}$ -NMR and GPC, with the analytical results shown below.

Copolymer compositional ratio

p-hydroxystyrene:styrene:methoxyisobutyl methacrylate =  
72.0:15.7:12.3

Mw = 15,700

5 Mw/Mn = 1.62

This polymer is designated Polymer A.

Synthesis Example 2

In a 2-liter flask were admitted 125.0 g of  
10 p-acetoxystyrene, 25.5 g of styrene, 11.9 g of ethoxyisobutyl  
methacrylate and 400 g of toluene as a solvent. The reactor  
was cooled to -70°C in a nitrogen atmosphere, whereupon  
vacuum deaeration and nitrogen flow were repeated three  
times. The reactor was warmed up to room temperature, 7.2 g  
15 of AIBN was added as a polymerization initiator, and the  
reactor was further heated to 60°C, at which reaction was  
effected for 20 hours. The reaction solution was  
concentrated to a 1/2 volume and poured into a mixture of 4.8  
liters methanol and 0.2 liter water for precipitation. The  
20 resulting white solids were filtered and vacuum dried at  
40°C, obtaining 177 g of a white polymer. The polymer was  
dissolved in a mixture of 0.3 liter methanol and 0.35 liter  
tetrahydrofuran again, to which 200 g of triethylamine and 40  
g of water were added to effect deblocking reaction. The  
25 reaction solution was neutralized with acetic acid,  
concentrated, and dissolved in 0.5 liter of acetone.  
Following precipitation, filtration and drying in the same  
way as above, 117 g of a white polymer was obtained.

The polymer was analyzed by <sup>13</sup>C-NMR, <sup>1</sup>H-NMR and GPC,  
30 with the analytical results shown below.

Copolymer compositional ratio

p-hydroxystyrene:styrene:ethoxyisobutyl methacrylate =  
72.3:13.8:13.9

Mw = 16,100

35 Mw/Mn = 1.63

This polymer is designated Polymer B.

### Synthesis Example 3

In a 2-liter flask were admitted 126.3 g of p-acetoxystyrene, 63.4 g of t-butoxystyrene, 10.3 g of methoxyisobutyl methacrylate and 400 g of toluene as a solvent. The reactor was cooled to -70°C in a nitrogen atmosphere, whereupon vacuum deaeration and nitrogen flow were repeated three times. The reactor was warmed up to room temperature, 8.0 g of AIBN was added as a polymerization initiator, and the reactor was further heated to 60°C, at which reaction was effected for 20 hours. The reaction solution was concentrated to a 1/2 volume and poured into a mixture of 4.8 liters methanol and 0.2 liter water for precipitation. The resulting white solids were filtered and vacuum dried at 40°C, obtaining 177 g of a white polymer. The polymer was dissolved in a mixture of 0.3 liter methanol and 0.35 liter tetrahydrofuran again, to which 200 g of triethylamine and 40 g of water were added to effect deblocking reaction. The reaction solution was neutralized with acetic acid, concentrated, and dissolved in 0.5 liter of acetone. Following precipitation, filtration and drying in the same way as above, 122 g of a white polymer was obtained.

The polymer was analyzed by  $^{13}\text{C}$ -NMR,  $^1\text{H}$ -NMR and GPC, with the analytical results shown below.

#### Copolymer compositional ratio

p-hydroxystyrene:t-butoxystyrene:methoxyisobutyl methacrylate = 74.7:19.1:6.2

Mw = 14,900

Mw/Mn = 1.57

This polymer is designated Polymer C.

### Synthesis Example 4

In a 2-liter flask were admitted 121.1 g of p-acetoxystyrene, 58.4 g of t-amylloxystyrene, 10.0 g of methoxyisobutyl methacrylate and 400 g of toluene as a solvent. The reactor was cooled to -70°C in a nitrogen atmosphere, whereupon vacuum deaeration and nitrogen flow were repeated three times. The reactor was warmed up to room

temperature, 7.9 g of AIBN was added as a polymerization initiator, and the reactor was further heated to 60°C, at which reaction was effected for 20 hours. The reaction solution was concentrated to a 1/2 volume and poured into a mixture of 4.8 liters methanol and 0.2 liter water for precipitation. The resulting white solids were filtered and vacuum dried at 40°C, obtaining 175 g of a white polymer. The polymer was dissolved in a mixture of 0.3 liter methanol and 0.35 liter tetrahydrofuran again, to which 200 g of triethylamine and 40 g of water were added to effect deblocking reaction. The reaction solution was neutralized with acetic acid, concentrated, and dissolved in 0.5 liter of acetone. Following precipitation, filtration and drying in the same way as above, 118 g of a white polymer was obtained.

The polymer was analyzed by <sup>13</sup>C-NMR, <sup>1</sup>H-NMR and GPC, with the analytical results shown below.

Copolymer compositional ratio

p-hydroxystyrene:t-amyloxystyrene:methoxyisobutyl methacrylate = 76.0:17.2:6.8

Mw = 17,000

Mw/Mn = 1.58

This polymer is designated Polymer D.

Synthesis Example 5

In a 2-liter flask were admitted 184.9 g of p-acetoxystyrene, 101.1 g of 2-ethyl-2-adamantyl methacrylate, 14.0 g of methoxyisobutyl methacrylate and 850 g of toluene as a solvent. The reactor was cooled to -70°C in a nitrogen atmosphere, whereupon vacuum deaeration and nitrogen flow were repeated three times. The reactor was warmed up to room temperature, 16.0 g of AIBN was added as a polymerization initiator, and the reactor was further heated to 57°C, at which reaction was effected for 20 hours. The reaction solution was concentrated to a 1/2 volume and poured into a mixture of 4.8 liters methanol and 0.2 liter water for precipitation. The resulting white solids were filtered and vacuum dried at 40°C, obtaining 256 g of a white polymer.

The polymer was dissolved in a mixture of 0.45 liter methanol and 0.50 liter tetrahydrofuran again, to which 300 g of triethylamine and 60 g of water were added to effect deblocking reaction. The reaction solution was neutralized with acetic acid, concentrated, and dissolved in 0.5 liter of acetone. Following precipitation, filtration and drying in the same way as above, 179 g of a white polymer was obtained.

The polymer was analyzed by  $^{13}\text{C}$ -NMR,  $^1\text{H}$ -NMR and GPC, with the analytical results shown below.

10     Copolymer compositional ratio

p-hydroxystyrene:2-ethyl-2-adamantyl methacrylate:

methoxyisobutyl methacrylate = 73.8:20.1:6.1

Mw = 15,900

Mw/Mn = 1.59

15             This polymer is designated Polymer E.

Synthesis Example 6

In a 2-liter flask were admitted 180.2 g of p-acetoxystyrene, 98.9 g of 2-methyl-2-adamantyl methacrylate, 14.7 g of methoxyisobutyl methacrylate and 850 g of toluene as a solvent. The reactor was cooled to  $-70^\circ\text{C}$  in a nitrogen atmosphere, whereupon vacuum deaeration and nitrogen flow were repeated three times. The reactor was warmed up to room temperature, 16.3 g of AIBN was added as a polymerization initiator, and the reactor was further heated to  $57^\circ\text{C}$ , at which reaction was effected for 20 hours. The reaction solution was concentrated to a 1/2 volume and poured into a mixture of 4.8 liters methanol and 0.2 liter water for precipitation. The resulting white solids were filtered and vacuum dried at  $40^\circ\text{C}$ , obtaining 248 g of a white polymer. The polymer was dissolved in a mixture of 0.45 liter methanol and 0.50 liter tetrahydrofuran again, to which 300 g of triethylamine and 60 g of water were added to effect deblocking reaction. The reaction solution was neutralized with acetic acid, concentrated, and dissolved in 0.5 liter of acetone. Following precipitation, filtration and drying in the same way as above, 173 g of a white polymer was obtained.

The polymer was analyzed by  $^{13}\text{C}$ -NMR,  $^1\text{H}$ -NMR and GPC, with the analytical results shown below.

Copolymer compositional ratio

p-hydroxystyrene:2-methyl-2-adamantyl methacrylate:

5 methoxyisobutyl methacrylate = 70.5:22.5:7.0

Mw = 14,100

Mw/Mn = 1.62

This polymer is designated Polymer F.

10 Comparative Synthesis Examples

For comparison purposes, ternary polymers were synthesized by the same procedure as the foregoing Synthesis Examples. Their composition and analytical results are shown below.

15 Copolymer compositional ratio

p-hydroxystyrene:styrene:ethoxyethyl methacrylate =

70.6:15.9:13.5

Mw = 16,900

Mw/Mn = 1.63

20 This polymer is designated Polymer G.

Copolymer compositional ratio

hydroxystyrene:t-amylloxystyrene:tetrahydropyranyl

methacrylate = 75.1:14.7:10.2

Mw = 17,200


25 Mw/Mn = 1.59

This polymer is designated Polymer H.


Polymers A to H obtained in Synthesis Examples and Comparative Synthesis Examples are shown below.

30







Polymer A




Polymer B




Polymer C




Polymer D




Polymer E



Polymer F




Polymer G




Polymer H

## Experiment


Homopolymers having recurring units of the formulae (1)-1 to (1)-4, (H-1) and (H-2), shown below, were synthesized by a conventional radical polymerization process and measured for pyrolysis temperature by TG/DTA, with the results shown in Table 1. It is noted that measurement was done by heating from 70°C to 400°C at a rate of 1°C/min and determining the temperature at which the polymer first marked a weight loss as the pyrolysis temperature. Additionally, the incipient endothermic temperature and endothermic peak temperature were measured.




(1)-1




(1)-2




(1)-3



(1)-4



(H-1)



(H-2)

Table 1

Polymer	Mw	Pyrolysis temperature	Incipient endothermic temperature	Endothermic peak temperature
(1)-1	10,200	162° C	180° C	201° C
(1)-2	9,700	157° C	165° C	193° C
(1)-3	9,600	155° C	163° C	198° C
(1)-4	11,000	156° C	165° C	199° C
(H)-1	10,500	139° C	145° C	188° C
(H)-2	11,000	140° C	147° C	188° C

It is seen from the data that the polymers of alkoxyalkyl (meth)acrylates within the scope of the invention have a pyrolysis temperature above 150° C, suggesting that resist compositions comprising these polymers remain stable during shelf storage.

Examples 1-6 & Comparative Examples 1-2

Resist compositions were prepared according to the formulation shown in Tables 2 and 3. The polymers are Polymers A to H obtained in the above Synthesis Examples and Comparative Synthesis Examples, and the remaining components listed in Tables 2 and 3 have the following meaning.

PAG1: (4-butoxyphenyl)diphenylsulfonium 10-camphorsulfonate

PAG2: (4-tert-butylphenyl)diphenylsulfonium 4-(4'-methylphenylsulfonyloxy)phenylsulfonate

Dissolution inhibitor A: bis(4-(2-tetrahydropyranyloxy)-phenyl)methane

Basic compound A: tris(2-methoxyethyl)amine

Surfactant A: FC-430 (Sumitomo 3M Co., Ltd.)

Surfactant B: Surflon S-381 (Asahi Glass Co., Ltd.)

Solvent A: propylene glycol methyl ether acetate

Solvent B: ethyl lactate

Table 2

Component (pbw)	Example 1	Example 2	Example 3	Example 4
Polymer A	80	-	-	-
Polymer B	-	80	-	-
Polymer C	-	-	80	-
Polymer D	-	-	-	80
PAG1	2	2	2	2
PAG2	1	1	1	1
Dissolution inhibitor A	-	-	-	-
Basic compound A	0.2	0.2	0.2	0.2
Surfactant A	0.07	0.07	0.07	0.07
Surfactant B	0.07	0.07	0.07	0.07
Solvent A	300	300	300	300
Solvent B	130	130	130	130

Table 3

Component (pbw)	Example 5	Example 6	Comparative Example 1	Comparative Example 2
Polymer E	80	-	-	-
Polymer F	-	80	-	-
Polymer G	-	-	80	-
Polymer H	-	-	-	80
PAG1	2	2	2	1
PAG2	1	1	1	1
Dissolution inhibitor A	-	-	-	-
Basic compound A	0.2	0.2	0.2	0.2
Surfactant A	0.07	0.07	0.07	0.07
Surfactant B	0.07	0.07	0.07	0.07
Solvent A	300	300	300	300
Solvent B	130	130	130	130

The resist solutions thus obtained were each filtered through a 0.2- $\mu$ m Teflon filter. These resist solutions were spin-coated onto silicon wafers, then baked on a hot plate at 100°C for 90 seconds to give resist films having a thickness  
5 of 0.4  $\mu$ m. The resist films were exposed using an excimer laser stepper NSR2005EX (Nikon Corp., NA 0.6), then baked at 110°C for 90 seconds (post-exposure baking: PEB), and developed with a solution of 2.38% tetramethylammonium hydroxide in water, thereby giving positive patterns  
10 (Examples 1-6 and Comparative Examples 1-2).

The resulting resist patterns were evaluated as described below.

#### Resist pattern evaluation

The exposure dose which provides a 1:1 resolution at  
15 the top and bottom of a 0.15- $\mu$ m line-and-space pattern was the optimum exposure dose (sensitivity Eop). The minimum line width of a line-and-space pattern which was ascertained separate at this dose was the resolution of a test resist. The shape in cross section of the resolved resist pattern was  
20 examined under a scanning electron microscope.

The PED stability of a resist was evaluated by effecting post-exposure bake (PEB) after 24 hours of holding from exposure at the optimum dose and determining a variation in line width. The less the variation, the greater is the  
25 PED dimensional stability.

The shelf stability of the resist composition was examined by passing a resist composition as prepared through a filter, holding the composition in a light-shielded state at 20°C for 30 days, then subjecting to coating, exposure and  
30 development steps under the same conditions as above, and observing a cross section of the resist pattern again under a SEM. The resists which remained unchanged, changed somewhat and changed noticeably in sensitivity, resolution and pattern shape from the fresh resist were judged "Good," "Fair" and  
35 "Poor," respectively.

The results are shown in Table 4.

Table 4

	Sensitivity (mJ/cm <sup>2</sup> )	Resolution (μm)	Profile	24 hr PED stability (nm)	Shelf stability @20° C/30days
Example 1	28	0.12	rectangular	-6	Good
Example 2	25	0.12	rounded head	-9	Fair
Example 3	27	0.12	rectangular	-5	Good
Example 4	25	0.11	rounded head	-8	Good
Example 5	29	0.11	rectangular	-5	Good
Example 6	30	0.12	rectangular	-4	Good
Comparative Example 1	29	0.12	rounded head	-20	Poor
Comparative Example 2	30	0.13	rounded head	-24	Poor

There have been described resist compositions in which  
5 a polymer using a thermally stable alkoxyalkyl (meth)acrylate  
as a reactive group which is decomposable under the action of  
an acid to increase solubility in alkali is blended as the  
base resin. The compositions have advantages including a  
practical level of shelf stability, a significantly enhanced  
10 contrast of alkali dissolution rate before and after  
exposure, a high sensitivity, and a high resolution over a  
wide baking temperature range. The compositions are best  
suited as a chemically amplified resist material for  
micropatterning in the manufacture of VLSI.

15 Japanese Patent Application No. 2002-195740 is  
incorporated herein by reference.

Although some preferred embodiments have been  
described, many modifications and variations may be made  
thereto in light of the above teachings. It is therefore to  
20 be understood that the invention may be practiced otherwise  
than as specifically described without departing from the  
scope of the appended claims.